

C-TAR MELT

PRODUCT SPECIFICATION

C-TAR MELT

AUGUST 2, 2011

RINSEABLE TAR REMOVER

DESCRIPTION AND USE

C-Tar Melt is a blend of water soluble, easily rinseable, non hazardous ingredients. C-Tar Melt is safe for wood, metal, and masonry surfaces and will not raise the grain or cause discoloration of the surface. The product will aid in the separation of tar residue from rinse water if runoff is contained and stored for a short period of time.

ADVANTAGES

- * Power penetration and softening action
- * Biodegradable
- * Will not harm the skin. (Constant exposure may cause dryness).

LIMITATIONS

- * Will cause rubber to swell
- * Some softening of the paint may occur (ceases upon rinsing). Always test before prolonged exposure.

TECHNICAL DATA

Appearance & Odor: White color, hydrocarbon odor.

Physical State: Liquid

pH: 7.5

Vapor Pressure (mmHg): N/A

Vapor Density (air=1): N/A

Boiling Point: N/A

Freezing/Melting Point: N/A

Specific Gravity (water =1): .850

Evaporation Rate: N/A

Solubility in Water: Negligible

PREPARATION

Protect adjacent and surrounding surfaces from exposure to the cleaning solution when necessary.

SURFACE & AIR TEMPERATURES

Excessively high or low temperatures will produce poor results and possible harm. Best cleaning results are obtained when air and surface temperatures are 40° F or above. Do not clean when temperatures are below freezing or will be overnight. If freezing conditions exist, allow adequate time for surface to thaw. If air temperatures exceed 90° F, flash cool the surface with water before applying product. Do not allow product to dry on a hot surface.

PRE-TESTING

Always test prior to beginning full-scale cleaning operations. Testing should confirm cleaning effectiveness on each type of surface and stain designated to be removed. Testing

also determines the desired dwell time and any potential for adverse reactions with adjacent materials. Allow test panels to dry thoroughly before evaluating final appearance and results.

DILUTION

Use undiluted (straight).

APPLICATION INSTRUCTIONS

C-Tar Melt is used straight; do not dilute this product with water. The best method of tar removal from a painted vehicle is by putting a small amount on a cloth and wiping. Two applications, one following the other after a short soak period will sometimes out perform a single application and mechanical removal. Dwell times will vary with thickness of the coating to be stripped. C-Tar Melt can remove many materials in a fifteen minute time span. Heavy layers may be removed with an overnight soak. Craftsmanship determines the appropriate pressures for rinsing. A thorough rinse job is always recommended, however, our chemistry never requires flooding a wall. Pressures that mark or damage the surface should be avoided. When in doubt, follow the manufacturers recommended P.S.I. for the substrate on which you are working. Proper ventilation should always be a consideration when long term exposure will occur. It is recommended that skin contact be kept to a minimum and at least a water rinse be used after contact

COVERAGE RATES

Coverage rates will vary from 100 - 250 sq. ft. per gallon depending on the surface porosity, texture and severity of staining.

PRECAUTIONARY MEASURES

Always wear goggles and gloves when handling this product. Keep off of skin and clothing. If material comes in contact with clothing, wash before reuse. The product contains Petroleum Hydrocarbon. Do not get in eyes, on skin or clothing. Avoid breathing fumes. Keep container closed when not in use. Use with adequate ventilation. Applicators should wear boots, gloves, face shields and/or goggles made of solvent resistant materials to avoid splash to bare skin and eyes. Though the potential for fuming of C-Tar Melt is minimal, take precautions to avoid exposing building occupants to fumes. Dispose of empty containers according to federal, state, and local requirements. Avoid drifting of material or rinse water onto autos and pedestrians by protecting or diverting such traffic. Do not dilute C-Tar Melt. Do not use for any other applications other than specified. Do not remove label. Read Material Safety Data Sheet for additional safety and health hazard information prior to use.

EaCo Chem. Inc.
765 COMMERCE AVE
NEW CASTLE PA 16101

PHONE: (800) 313-8505
FAX: (724) 656-0757
www.eacochem.com



C-TAR MELT

PRODUCT SPECIFICATION
C-TAR MELT
AUGUST 2, 2011

RINSEABLE TAR REMOVER

SPILL OR LEAK PROCEDURES

Check with the state, local, or federal regulations for waste disposal methods in the area. Wear proper protective equipment while doing cleanup. For large spills, dike and contain for intended use. For small spills, use a chemical absorbent product and place in approved container for disposal.

CONTAINER HANDLING/STORAGE

Store the product in a cool dry place. Vent bung cap before opening. Keep container tightly closed when not in use. Do not use pressure to empty container. Wash thoroughly after handling. Do not use container as dilution or rinsing vessel. Do not cut, grind or weld on or near container. Empty containers retain residue and must be handled as if full.

INSTRUCTIONS IN CASE OF CONTACT OR EXPOSURE

Eyes: Flood with water fifteen minutes. Seek immediate medical attention.

Skin: Wash off with soap and water. If irritation persists, call physician.

Inhalation: Drink lots of water. Seek immediate medical attention.

Ingestion: Remove to fresh air. If irritation persists, call physician.

NOTICE

This product has been classified in accordance with the hazard criteria of the CFR.

DISCLAIMER

The information herein is given in good faith, but no warranty, either expressed or implied, is made. Final determination of the suitability of any material is the sole responsibility of the user. All materials may present unknown hazards and should be used with caution. Although certain hazards are described herein we cannot be sure or guarantee these are the only hazards, which exist.

CUSTOMER SERVICE

Factory personnel are available for assistance at 800-313-8505 and will send you additional information on products as necessary.

